



Honewash® WH101

Features

- Applicable to the pretreatment or one-bath scouring and dyeing process of polyester warp-knitted, weft-knitted fabrics and their blends.
- It exhibits excellent emulsifying and dispersing performance under neutral, weakly acidic and alkaline conditions.
- It is highly effective against disperse chemical fiber oils and other substances, preventing oil agents from fouling the equipment and causing secondary staining on the fabric surface.
- In the one-bath degreasing and dyeing process, it eliminates specks and uneven dyeing caused by oil agent and oligomer fouling, thus improving processing quality.

Product parameters

Appearance	pH	Ionicity
Ligh yellow liquid	6.0-8.0	Nonionic

Application

Recommended Application

Degreasing process for one-bath scouring & dyeing of polyester knits:

WH101: 0.3-1.0 g/L

Dyes: X

Temperature: 120-130℃, Treatment time: 30-60 min, then cool down, rinse, and unload the goods.

Degreasing process for polyester embroidery fabrics and the like:

WH101: 0.3-1.5 g/L

Run at room temperature for 10 min after adding the degreaser, then heat up to 80-100℃ and treat for 30-60 min, followed by overflow rinsing and unloading.

Note: The specific process parameters shall be adjusted by the user according to trials as appropriate.

Storage

At room temperature the product can be stored in the original packaging for 12 months. The product should be stored sealed and packed in a cool, ventilated, dry environment, avoid the products directly exposing to the air or the product is stored for a long time in extreme hot and cold environments. Long time high - temperature environments may lead to product deterioration, color change!



Packaging

120 kg per barrel

Safety

Before using any of our products, be sure to consult the latest Material Safety Data Sheet (MSDS) for the product. You may contact our relevant personnel to obtain the MSDS and other safety-related information for the product. Please note particularly that prior to using any product mentioned in this document, you shall obtain complete product safety information in advance and take necessary safety precautions to ensure safety during use.

Disclaimer

The information, recommendations and suggestions provided herein are all based on the knowledge and experience currently available to us. We do not expressly or impliedly promise or guarantee that the effects described herein can be achieved under actual end-use conditions, nor shall we assume any relevant obligations or legal liabilities therefor. We reserve the right to adjust relevant contents in light of technological progress and development. The user shall bear full responsibility, determine whether the materials, products, recommendations or suggestions provided by us are suitable for its specific purposes, and confirm the safety and applicability of all components under final end-use conditions through sufficient tests and analyses. Since we cannot control the actual use of the products by the user, the user shall independently bear full responsibility for its acts of use. We shall not be liable for any losses arising from improper or incorrect use of the products. No data herein may be reproduced without the prior written permission of our company.